



## SX744:CM488

### Silane crosslinkable medium density polyethylene for high temperature pressure pipes

Material SX744 is a silane grafted MDPE compound, curable by exposure to moist conditions, and possessing good extrusion properties at high output rates. The graft component SX744 is mixed with a crosslinking catalyst masterbatch CM488 generally in the ratio 95:5.

The highly crosslinked materials produced by the two-component system possess excellent impact strength, ESCR, creep and internal pressure resistance under ambient and elevated temperature conditions.

These materials have been formulated for hot and cold water pressure pipes and are easily extrudable on conventional polyethylene extrusion lines.

Test	Test method	Unit	Typical value
<b>Physical properties and mechanical properties</b>			
Density	BS 2782 Pt. 6 Mtd 620A-D	g/cm <sup>3</sup>	0.941
Melt flow rate (190°C/2.16kg)	AEI Method	g/10min	1.3
Tensile strength	IEC 60811-1-1	N/mm <sup>2</sup>	24
Elongation at break	IEC 60811-1-1	%	550
1% Secant Modulus	BS 2782-3 METHOD 320A	N/nm <sup>2</sup>	650
Gel content	ASTM D2765-01 (2006)	%	72
<b>Cure assessment by hot set test (forced cured at 80°C in water)</b>			
Elongation under load (20N/cm <sup>2</sup> at 200°C)	IEC 60811-2-1	%	55
Permanent elongation after cooling	IEC 60811-2-1	%	0

#### Pressure testing

Pipe produced from SX744:CM488 has been shown to satisfy the internal pressure requirements of DIN 16892 and other international specifications.

© AEI Compounds Limited, Sandwich Industrial Estate, Sandwich, Kent, CT13 9LY

Telephone +44 (0) 1304 616171

Facsimile +44 (0) 1304 616170

Email sales@aeicompounds.co.uk

Website www.aeicompounds.com

A division of



# SX744:CM488

## Recommended processing and handling conditions

### Extruder Screw

The use of a high compression polyethylene type screw of 20-25 L:D ratio and compression ratio 2.5:1 to 3:1 is recommended.

### Extruder temperature conditions

As a guide the following temperature profile is recommended:-

Zone 1	Zone 2	Zone 3	Zone 4	Head	Die
140°C	160°C	175°C	190°C	200°C	200°C

This profile will vary slightly depending on extruder type, head design and output.

**Screw water temperature** approx 60°C

**Recommended screen pack** 30, 50, 100 (mesh apparatus per linear inch) or 600, 150, 600 micron

### Draw down ratio

If extrusion conditions require extrudate draw down, this should not exceed a ratio of 2:1.

### Crosslinking or cure

If properly processed the material has the capacity of crosslinking under ambient conditions.

Should accelerated cure times be required, then any of the following methods may be employed.

- Immersion in water at 80°C
- Flushing with water at 80°C
- Exposure to steam at 90°C (as in a sauna)

### Catalyst and colour masterbatches

CM488 catalyst masterbatch is normally added at 5% to 95% of SX744 graft.

Addition of approved colour masterbatches, including black, up to a maximum of 1%, has no detrimental effect on the properties or crosslinking capability.

It is recommended that all masterbatches, including those containing the catalyst, should be thoroughly dried at 60°C for 8 hours or at 80°C for 4 hours.

### Storage and shelf life

SX744 normally has shelf life of at least 6 months from the date of manufacture. The storage of silane crosslinkable compounds in cool dry conditions will maximise useful shelf life. Other precautions are:-

- Packaging should remain sealed.
- Avoid temperature above 25°C.
- Avoid storage outside and in direct sunlight.
- Use within 8 hours of opening packaging.

### Form and packaging

Form – pellets

Packaging – the following possibilities are available:-

- Moisture resistant sacks containing 25kg.
- Boxes with a moisture resistant heat sealed liner containing approximately 125kg, 500kg or 1000kg.

© AEI Compounds Limited, Sandwich Industrial Estate, Sandwich, Kent, CT13 9LY

Telephone +44 (0) 1304 616171

Facsimile +44 (0) 1304 616170

Email sales@aeicompounds.co.uk

Website www.aeicompounds.com

A division of



Whilst this document has been prepared in good faith, AEI Compounds Limited accepts no liability of any kind to any person in respect of its contents or any use made thereof. Neither must it be assumed that any use will not infringe any patent. This document shall not form part of any contract with a customer.